

Acciai laminati

Norma e tipo di acciaio	Spessore nominale della membratura					
	t ≤ 40 mm			40 mm < t ≤ 80 mm		
	$f_{yk}$ [N/mm <sup>2</sup> ]	$f_{tk}$ [N/mm <sup>2</sup> ]	$\sigma_{fa}$ [N/mm <sup>2</sup> ]	$f_{yk}$ [N/mm <sup>2</sup> ]	$f_{tk}$ [N/mm <sup>2</sup> ]	$\sigma_{fa}$ [N/mm <sup>2</sup> ]
EN 10025-2						
S 235	235	360	204,35	215	360	186,96
S 275	275	430	239,13	255	410	221,74
S 355	355	510	308,70	335	470	291,30
S 450	440	550	382,61	420	550	365,22